

DUROFLEX TECHNICAL DATA SHEET

Force of adhesion to concrete		MEL 052	≥2N/cm
Force of adhesion to metals		MEL 052	≥4N/cm
Water vapor permeability		NF T 30-018	=2.5g/m ² /24Std
Spill resistance	Seal 5°C Seal 70°C	ISO7390 ISO7390	0mm ≤3mm
Temperature	Application Service Breakdown		+5°C≤T≤+40°C -30°C≤T≤+80°C >250°C
Bend	ECCA 7 (0≤T BEND≤1)	MEL 052	≥2N/cm
Grid	MEK resistant		>50 double rubs
Friction resistance	ILA 15		OK
UV resistance	ASTM G 154 (500 hours, UV-313 4h) 60°C/Condensation, 4h. 40°C		OK
Fire reaction classification			M1

*If the product is stored below 0°C, it must be stored for 24 hours at 20°C before application. Temperature above 5°C is recommended for installation.

